

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 1 245 642 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

02.10.2002 Bulletin 2002/40

(51) Int Cl.7: **C08L 83/04**, C08J 9/26,  
H01B 3/46, H01L 21/316,  
H01L 21/312

(21) Application number: **02251958.1**

(22) Date of filing: **19.03.2002**

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 27.03.2001 KR 2001015884

14.09.2001 KR 2001056798

(71) Applicant: **SAMSUNG ELECTRONICS CO., LTD.**  
Suwon-City, Kyungki-do 442-742 (KR)

(72) Inventors:

- Lyu, Yi Yeol  
Yusung-Gu, Daejun-Shi, 305-761 (KR)
- Yim, Jin Heong  
Yusung-Gu, Daejun-Shi, 305-390 (KR)

- Jeong, Hyun Dam,  
111/802 Evergreen Byucksan Apt.  
Suwon-Shi, Kyungki-Do, 442-707 (KR)
- Kim, Jung Hyung, 6/202 Joint Control Apartment  
Daejun-Shi, 305-340 (KR)
- Mah, Sang Kook  
Yongdungpo-Gu, Seoul, 150-762 (KR)
- Nah, Eun Ju  
Chung-Gu, Daejun-Shi, 301-150 (KR)
- Hwang, Sun Il  
Chung-Gu, Daejun-Shi 301-142 (KR)

(74) Representative: Kyle, Diana  
Elkington & Fife  
Prospect House  
8 Pembroke Road  
Sevenoaks Kent TN13 1XR (GB)

(54) **Siloxane-based resin and method for forming an insulating film between interconnecting layers in wafers**

(57) Disclosed herein are siloxane-based resins prepared by hydrolyzing and polycondensing cyclic and/or cage-shape siloxane compounds, optionally with at least one silane compound, in an organic solvent in the presence of a catalyst and water. Also, disclosed herein

are methods for forming insulating film between interconnect layers in semiconductor devices by using the siloxane-based resins thus prepared as low dielectric insulating materials.

**EP 1 245 642 A1**

## Description

## FIELD OF THE INVENTION

5 [0001] The present invention relates to a siloxane-based resin and a method for forming insulating film between interconnect layers in semiconductor devices by using the same. More specifically, the present invention relates to a siloxane-based resin prepared by hydrolyzing and polycondensing cyclic and/or cage-shape siloxane compounds, optionally with at least one silane compound, in an organic solvent in the presence of a catalyst and water. The present invention also relates to a method for forming insulating film between interconnect layers in semiconductor devices, 10 wherein the siloxane-based resin described above is used as low dielectric insulating materials.

## BACKGROUND OF THE INVENTION

15 [0002] As the circuit density in multilevel integrated circuit devices increases, the reduction of feature size in a semiconductor device is strongly required. But, there are fatal problems such as  $R(\text{resistance}) \times C(\text{capacitance})$  delay due to crosstalk between interconnect lines. Therefore, dielectric constant of interlayer insulating films should be lowered so as to decrease the RC delay as much as possible. For this purpose, there have been various attempts to develop low dielectric materials for use in the insulating film.

20 [0003] For example, polysilsesquioxanes having dielectric constant of approximately 2.5~3.1 has replaced  $\text{SiO}_2$  having dielectric constant of 4.0 in chemical vapor deposition(CVD). Such polysilsesquioxanes can be also applied to a spin coating method due to its excellent planation property.


[0004] The polysilsesquioxanes as well as preparing methods thereof are well known in the art. For example, US Patent No. 3,615,272 discloses a method for preparing completely condensed soluble hydrogensilsesquioxane resins, which comprises the steps of condensing trichlorosilanes in a sulfuric acid medium, and then washing the resulting resins with water or aqueous sulfuric acid. US Patent No. 5,010,159 discloses a method for synthesizing soluble condensed hydridosilicon resins, which comprises the steps of hydrolyzing hydridosilanes in an arysulfuric acid hydrate-containing hydrolysis medium, and then contacting the resulting resins with a neutralizing agent. US Patent No. 6,232,424 describes a highly soluble silicone resin composition having excellent solution stability, which was prepared by hydrolyzing and polycondensing tetraalkoxysilane, organosilane and organotrialkoxysilane monomers in the presence of water and a catalyst. US Patent No. 6,000,339 teaches that a silica-based compound, which may be useful for improving the resistance and physical properties as well as thickness of a coating film, can be obtained from a reaction of a monomer selected from the group consisting of alkoxysilane, fluorine-containing alkoxysilane and alkylalkoxysilane and a titanium- or zirconium-alkoxide compound in the presence of water and a catalyst. US Patent No. 5,853,808 describes that silsesquioxane polymers that are useful for preparing  $\text{SiO}_2$ -rich ceramic coatings can be obtained as the polymeric reaction products from the hydrolysis and condensation of organosilanes having a  $\beta$ -substituted alkyl group. 35

[0005] However, the prior polysilsesquioxane resins have not accomplished very low dielectric constant that is currently required for insulating film between interconnect layers in semiconductor devices. Additionally, they have been required to improve in mechanical properties, thermal stability, crack-resistance, and so on. 40

## SUMMARY OF THE INVENTION


45 [0006] A feature of the present invention is a method for forming low dielectric insulating film between interconnect layers in semiconductor devices by using a siloxane-based resin having very low dielectric constant, wherein the resin is obtained from the copolymerization of cyclic and/or cage-shape siloxane compounds optionally with one or more silane compounds.

[0007] An aspect of the present invention relates to siloxane-based resins that are prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1) and a cage-shape siloxane compound of any of formulas (2a)-(2c) in an organic solvent in the presence of a catalyst and water. 50




(1)


wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; p is an integer from 3 to 8; and m is an integer from 1 to 10;



(2a)




(2b)





in the above formulas (2a)-(2c), each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo; and  $n$  is an integer from 1 to 12.

[0008] Another aspect of the present invention relates to siloxane-based resins that are prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1) and a cage-shape siloxane compound of any of formulas (2a)-(2c), together with a silane compound of formula (3) and/or a silane compound of formula (4), in an organic solvent in the presence of a catalyst and water:




wherein,  $R$  is H,  $C_{1-3}$  alkyl,  $C_{3-10}$  cycloalkyl, or  $C_{6-15}$  aryl; each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo;  $p$  is an integer from 3 to 8; and  $m$  is an integer from 1 to 10;






(2b)




(2c)

in the above formulas 2(a)-2(c), each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo; and  $n$  is an integer from 1 to 12;




wherein, each of  $X_1$ ,  $X_2$ ,  $X_3$ , and  $X_4$  is, independently,  $C_{1-10}$  alkoxy, or halo;



wherein,  $R$  is  $H$ ,  $C_{1-3}$  alkyl,  $C_{3-10}$  cycloalkyl, or  $C_{6-15}$  aryl; and each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo.


[0009] Still another aspect of the present invention relates to siloxane-based resins that are prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1), together with a silane compound of formula (3) and/or a silane compound of formula (4), in an organic solvent in the presence of a catalyst and water.



wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; p is an integer from 3 to 8; and m is an integer from 1 to 10;






wherein, each of X<sub>1</sub>, X<sub>2</sub>, X<sub>3</sub>, and X<sub>4</sub> is, independently, C<sub>1-10</sub> alkoxy, or halo;



wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; and each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo.

[0010] Still another aspect of the present invention relates to siloxane-based resins that are prepared by hydrolyzing and polycondensing a cage-shape siloxane compound of any of formulas (2a)-(2c), together with a silane compound of formula (3) and/or a silane compound of formula (4), in an organic solvent in the presence of a catalyst and water:





in the above formulas (2a)-(2c), each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo; and  $n$  is an integer from 1 to 12;



wherein, each of  $X_1$ ,  $X_2$ ,  $X_3$ , and  $X_4$  is, independently,  $C_{1-10}$  alkoxy, or halo;



wherein,  $R$  is  $H$ ,  $C_{1-3}$  alkyl,  $C_{3-10}$  cycloalkyl, or  $C_{6-15}$  aryl; and each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo.


[0011] Still another aspect of the present invention relates to a method for forming insulating film between interconnect layers in semiconductor devices, the method comprising the steps of: providing a resinous solution by dissolving the siloxane-based resin described above in an organic solvent; coating a silicon wafer with the resinous solution; and heat-curing the resulting coating film.

[0012] All of the above features and other features of the present invention will be successfully achieved from the present invention described in the following.

#### DETAILED DESCRIPTION OF THE INVENTION

[0013] A siloxane-based resin of the present invention is prepared by hydrolyzing and polycondensing cyclic and/or cage-shape siloxane monomers, optionally with at least one silane monomer, in an organic solvent in the presence of a catalyst and water.




[0014] The cyclic siloxane monomers used in the present invention can be represented by the following formula (1):



wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; p is an integer from 3 to 8; and m is an integer from 1 to 10.

[0015] As can be seen from the above formula (1), two silicon atoms are linked to each other through an oxygen atom to form cyclic structure, and the terminal of each branch comprises at least one hydrolysable group. These cyclic siloxane monomers, for example, may be obtained from a hydrosilation reaction using a metal catalyst.

[0016] The cage-shape siloxane monomers used in the present invention can be represented by one of the following formulas (2a)-(2c):




in the above formulas (2a)-(2c), each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; and n is an integer from 1 to 12.

[0017] As can be seen from the above formulas (2a)-(2c), two silicon atoms are linked to each other through an oxygen atom to form cyclic structure, and the terminal of each branch comprises at least one hydrolysable group.

[0018] As the cage-shape siloxane monomers, commercially available ones whose terminal functional groups are

halogens can be used, without modification or after substitution of the terminal halogens with alkyl and/or alkoxy groups. Such substitution may be accomplished by any of standard methods well known in the art. For example, the substitution of the terminal halogens with alkoxy groups can be readily accomplished through reacting the halogenated cage-shape siloxane compound with an alcohol and a triethylamine.

[0019] On the other hand, the silane monomers used in the present invention can be represented by the following formula (3), in which Si has four hydrolysable substituents:



wherein, each of  $\text{X}_1$ ,  $\text{X}_2$ ,  $\text{X}_3$ , and  $\text{X}_4$  is, independently,  $\text{C}_{1-10}$  alkoxy, or halo.

[0020] Non-limiting examples of such silane monomer include tetra-n-butoxysilane, tetra-n-propoxysilane, tetraethoxysilane, tetramethoxysilane, tetrachlorosilane, tetrabromosilane, tetrafluorosilane, triethoxychlorosilane, and trimethoxychlorosilane.

[0021] Also, the other silane monomers represented by the following formula (4) can be used in the preparation of the siloxane-based resins of the present invention, in which Si has at least one hydrolysable substituent:



wherein, R is H,  $\text{C}_{1-3}$  alkyl,  $\text{C}_{3-10}$  cycloalkyl, or  $\text{C}_{6-15}$  aryl; and each of  $\text{X}_1$ ,  $\text{X}_2$ , and  $\text{X}_3$  is, independently,  $\text{C}_{1-3}$  alkyl,  $\text{C}_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo.

[0022] Non-limiting examples of such silane monomer include methyltriethoxysilane, methyltrimethoxysilane, methyltri-n-propoxysilane, phenyltrimethoxysilane, phenyltriethoxysilane, phenyltrichlorosilane, phenyltrifluorosilane, methyltrichlorosilane, methyltribromosilane, methyltrifluorosilane, triethoxysilane, trimethoxysilane, trichlorosilane, and trifluorosilane.

[0023] The siloxane-based resins of the present invention can be obtained as copolymeric products from the hydrolysis and polycondensation of the cyclic siloxane compound of formula (1) (hereinafter, referred to as siloxane compound (1)) and the cage-shape siloxane compound of formula (2) (hereinafter, referred to as siloxane compound (2)) in an organic solvent in the presence of a catalyst and water. Alternatively, the siloxane-based resins of the present invention can be prepared by hydrolyzing and polycondensing either or both of siloxane compounds (1) and (2), together with either or both of the silane compound of formula (3) (hereinafter, referred to as silane compound (3)) and the silane compound of formula (4) (hereinafter, referred to as silane compound (4)), in an organic solvent in the presence of a catalyst and water.

[0024] For the preparation of a binary copolymer from siloxane compounds (1) and (2), the molar ratio of compound (1) vs. compound (2) is between 0.1:99.9 and 99.9:0.1, preferably 5:95 and 50:50.

[0025] On the other hand, for the preparation of a ternary copolymer from both siloxane compounds (1) and (2), in conjunction with either silane compound (3) or (4), an amount of each compound ranges from 1 to 98mol%, respectively.

[0026] Moreover, a quaternary copolymer can be prepared by using both silane compounds (3) and (4) in conjunction with both siloxane compounds (1) and (2). At this time, each of the four compounds is used in an amount of 1-97mol%, respectively.

[0027] In the present invention, as siloxane monomers, both cyclic and cage-shape siloxane compounds are not always used in combination, and thus it is also possible to use either of the cyclic and cage-shape siloxane compounds.

[0028] Where cyclic siloxane compound (1) is solely used as a siloxane monomer, silane compound (3) is preferably copolymerized therewith to provide a binary copolymer, wherein the molar ratio of compound (1) vs. compound (3) is between 99.9:0.1 and 0.1:99.9, preferably 95:5 and 50:50. Alternatively, silane compound (4) can be additionally employed in the copolymerization to provide a ternary copolymer. This ternary copolymer contains 1-98mol% of compound (1), 1-98mol% of compound (3), and 1-98mol% of compound (4).

[0029] Similarly, where cage-shape siloxane compound (2) is solely used as a siloxane monomer, silane compound (4) is preferably copolymerized therewith to provide a binary copolymer, wherein the molar ratio of compound (2) vs. compound (4) is between 0.1:99.9 and 99.9:0.1, preferably 5:95 and 50:50. Alternatively, silane compound (3) can be further added to the copolymerization reaction to provide a ternary copolymer. This ternary copolymer contains 1-98mol% of compound (2), 1-98mol% of compound (3), and 1-98mol% of compound (4).

[0030] As the organic solvents used in the preparation of the siloxane-based resins according to the present invention, aromatic hydrocarbon solvent, aliphatic hydrocarbon solvent, ketone-based solvent, ether-based solvent, acetate-based solvent, alcohol-based solvent, silicon-based solvent, or mixtures thereof are preferred.

[0031] Exemplary catalysts used in the present invention include, without limitation, hydrochloric acid, nitric acid,

benzene sulfonic acid, oxalic acid, formic acid, potassium hydroxide, sodium hydroxide, triethylamine, sodium bicarbonate, pyridine, and mixtures thereof.

[0032] In the hydrolysis and polycondensation reaction according to the present invention, the molar ratio of the catalyst vs. monomers to be polymerized (inclusive of siloxane and silane compounds) is preferably between 0.00001: 1 and 10:1. Further, 0.1-1,000mol of water is added to 1mol of the monomers. Then, the hydrolysis and polycondensation are carried out at a temperature of 0-200°C, preferably 50-110°C, for 0.1-100hrs, preferably 3-48hrs.

[0033] The siloxane-based resins thus prepared have Mw of 3,000 to 500,000, preferably 3,000 to 100,000. Preferably, Si-OR content in the whole terminal groups represented by Si-OR and/or Si-R is more than 5mol%, wherein R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl. The siloxane-based resins of the present invention can be used as matrix precursors of insulating film between interconnect layers in semiconductor devices.

[0034] Particular method for forming insulating film between interconnect layers in semiconductor devices by using the siloxane-based resins according to the present invention is described below.

[0035] As mentioned above, a method for forming insulating film between interconnect layers in semiconductor devices of the present invention comprises the steps of: providing a resinous solution by dissolving the siloxane-based resin in an organic solvent; coating a silicon wafer with the resinous solution; and heating the coated wafer to cure the resin.

[0036] According to the present invention, the resinous solution can further comprise a porogen, which is a pore-generating material. Non-limiting examples of the porogen useful in the present invention include cyclodextrin and derivatives thereof described in Korean Patent Appln. No. 2001-15883, as well as polycaprolactone and derivatives thereof described in U.S. Patent No. 6,114,458. Preferred mixing ratio of the siloxane-based resin vs. porogen is between 99:1 and 30:70(w/w), more preferably 90:10 and 50:50(w/w).

[0037] Preferred organic solvents used in dissolution of the siloxane-based resin or a mixture of the siloxane-based resin and porogen to provide a resinous solution can be exemplified by, but are not limited to, aliphatic hydrocarbon solvents; aromatic hydrocarbon solvents such as anisole, mesitylene and xylene; ketone-based solvents such as methyl isobutyl ketone, 1-methyl-2-pyrrolidinone, cyclohexanone and acetone; ether-based solvents such as tetrahydrofuran and isopropyl ether; acetate-based solvents such as ethyl acetate, butyl acetate and propylene glycol methyl ether acetate; alcohol-based solvents such as isopropyl alcohol, butyl alcohol and octyl alcohol; amide-based solvents such as dimethylacetamide and dimethylformamide; silicon-based solvents; and mixtures thereof.

[0038] Upon preparing a resinous solution, the organic solvent should be used in a sufficient amount to apply the resin component evenly on the surface of a wafer. Thus, the organic solvent is added to the siloxane-based resin or to the mixture of the siloxane-based resin and porogen so that final concentration of the solid matter (inclusive of the siloxane-based resin and the porogen) is 0.1-80wt%, preferably 5-40wt%.

[0039] Non-limiting examples of the method for coating a silicon wafer with the resinous solution thus prepared include spin-coating, dip-coating, spray-coating, flow-coating, and screen-printing, while spin-coating is most preferred. For spin coating, the spin rate is controlled to be between 1,000 and 5,000rpm.

[0040] After the coating, the organic solvent is evaporated from the wafer so that a resinous film comprising the siloxane-based resin can deposit on the wafer. At this time, the evaporation may be carried out by simple air-drying, or by subjecting the wafer, at the beginning of following curing step, to a vacuum condition or mild heating (≤100°C).

[0041] Subsequently, the resinous film is cured by heating for 1-150min at a temperature of 150-600°C, preferably 200-450°C, so as to provide a insoluble, crack-free film. As used herein, by "crack-free film" is meant a film without any crack observed with an optical microscope at a magnification of 1000X. As used herein, by "insoluble film" is meant a film that is substantially insoluble in any solvent described as being useful for dissolving the siloxane-based resins.

[0042] The coating film thus formed was found to have dielectric constant below 3.0, preferably between 2.0 and 2.7, and so it is very useful as an insulating film between interconnect layers in semiconductor devices.


[0043] The present invention can be more clearly understood with referring to the following examples. It should be understood that the following examples are not intended to restrict the scope of the present invention in any manner.

#### Production Example 1: Synthesis of cyclic siloxane monomers


##### Production Example 1-1: Synthesis of monomer (A)

[0044] To a flask were added 10.0g(29.014mmol) of 2,4,6,8-tetramethyl-2,4,6,8-tetravinylcyclotetrasiloxane and 0.164g of platinum(O)-1,3-divinyl-1,1,3,3-tetramethyldisiloxane complex (solution in xylene), and then diluted with 300ml of diethylether. Next, the flask was cooled to -78°C, 17.29g(127.66mmol) of trichlorosilane was slowly added thereto, and then it was slowly warmed to room temperature. The reaction was continued at room temperature for 20hrs, and volatile materials were removed from the reaction mixture under a reduced pressure of about 0.1Torr. To the mixture was added 100ml of pentane and stirred for 1hr, and then the mixture was filtered through celite. From the filtrate was evaporated pentane under a reduced pressure of about 0.1Torr, to afford a liquid compound represented

by the following formula:




[0045] 10.0g(11.28mmol) of the liquid compound was diluted with 500ml of tetrahydrofuran, and 13.83g(136.71mmol) of triethylamine was added thereto. Thereafter, the mixture was cooled to -78°C, 4.38g(136.71mmol) of methyl alcohol was slowly added thereto, and then it was slowly warmed to room temperature. The reaction was continued at room temperature for 15hrs and filtered through celite, and then volatile materials were evaporated from the filtrate under a reduced pressure of about 0.1Torr. Subsequently, 100ml of pentane was added to the filtrate and stirred for 1hr, and then the mixture was filtered through celite to provide a clear colorless solution. Finally, pentane was evaporated from this solution under a reduced pressure of about 0.1Torr to afford monomer (A) represented by the following formula:



[0046] The results obtained from NMR analysis of monomer (A) dissolved in CDCl<sub>3</sub> are as follows:  
 1H-NMR(300MHz): δ 0.09(s, 12H, 4×-CH<sub>3</sub>), 0.52~0.64(m, 16H, 4×-CH<sub>2</sub>CH<sub>2</sub>-), 3.58(s, 36H, 4×-[OCH<sub>3</sub>]<sub>3</sub>)

#### Production Example 1-2: Synthesis of monomer (B)

[0047] To a flask were added 2.0g(8.32mmol) of 2,4,6,8-tetramethylcyclotetrasiloxane and 0.034g of platinum(O)-1,3-divinyl-1,1,3,3-tetramethyldisiloxane complex(solution in xylene), and then diluted with 100ml of toluene, followed by addition of 7.75g(33.36mmol) of trimethoxy(7-octene-1-yl)silane. Next, the flask was slowly warmed to 75°C. The reaction was continued at 75°C for 36hrs, and then volatile materials were removed therefrom under a reduced pressure of about 0.1Torr. To the reaction mixture was added 100ml of pentane and stirred for 1hr, and then the mixture was filtered through celite. Subsequently, pentane was evaporated from the filtrate under a reduced pressure of about 0.1Torr to afford monomer (B) represented by the following formula:




[0048] The results obtained from NMR analysis of monomer (B) dissolved in CDCl<sub>3</sub> are as follows:  
 1H-NMR(300MHz): δ 0.11(s, 12H, 4×-CH<sub>3</sub>), 0.48~0.53(m, 8H, 4×-CH<sub>2</sub>-), 0.86~0.90(m, 8H, 4×-CH<sub>2</sub>-), 1.15~1.71(m, 48H, 4×-[CH<sub>2</sub>]<sub>6</sub>), 3.58(s, 36H, 4×-[OCH<sub>3</sub>]<sub>3</sub>)

## Production Example 2: Synthesis of cage-shape siloxane monomers

## Production Example 2-1: Synthesis of monomer (C)

[0049] To a flask was added 10.0g(7.194mmol) of octa(chlorosilylethyl)-POSS(Polyhedral Oligomeric Silsesquioxane) and diluted with 500ml of tetrahydrofuran, followed by addition of 6.41g(63.310mmol) of triethylamine. Next, the flask was cooled to  $-78^{\circ}\text{C}$ , and 2.03g(63.310mmol) of methyl alcohol was slowly added thereto, and then it was slowly warmed to room temperature. The reaction was continued at room temperature for 20hrs, filtered through celite, and then volatile materials were evaporated from the filtrate under a reduced pressure of about 0.1Torr. Subsequently, 100ml of pentane was added to the filtrate and stirred for 1hr, and then the mixture was filtered through celite to provide a clear colorless solution. Finally, pentane was evaporated from this solution under a reduced pressure of about 0.1Torr to afford monomer (C) represented by the following formula:




[0050] The results obtained from NMR analysis of monomer (C) dissolved in CDCl<sub>3</sub> are as follows:

<sup>1</sup>H-NMR(300MHz):  $\delta$  0.11(s, 48H, 8  $\times$  -[CH<sub>3</sub>]<sub>2</sub>), 0.54~0.68(m, 32H, 8  $\times$  -CH<sub>2</sub>CH<sub>2</sub>-), 3.43(s, 24H, 8  $\times$  -OCH<sub>3</sub>)

## Production Example 2-2: Synthesis of monomer (D)

[0051] To a flask was added 10.0g(6.438mmol) of octa(dichlorosilylethyl)-POSS and diluted with 500ml of tetrahydrofuran, followed by addition of 11.47g(113.306mmol) of triethylamine. Next, the flask was cooled to  $-78^{\circ}\text{C}$ , and 3.63g(113.306mmol) of methyl alcohol was slowly added thereto, and then it was slowly warmed to room temperature. The reaction was continued at room temperature for 20hrs, filtered through celite, and then volatile materials were evaporated from the filtrate under a reduced pressure of about 0.1Torr. Subsequently, 100ml of pentane was added to the filtrate and stirred for 1hr, and then the mixture was filtered through celite to provide a clear colorless solution. Finally, pentane was evaporated from this solution under a reduced pressure of about 0.1Torr to afford monomer (D) represented by the following formula:




[0052] The results obtained from NMR analysis of monomer (D) dissolved in CDCl<sub>3</sub> are as follows:

<sup>1</sup>H-NMR(300MHz):  $\delta$  0.12(s, 24H, 8  $\times$  -CH<sub>3</sub>), 0.56~0.70(m, 32H, 8  $\times$  -CH<sub>2</sub>CH<sub>2</sub>-),

3.46(s, 48H, 8x-[OCH<sub>3</sub>]<sub>2</sub>)

### Production Example 2-3: Synthesis of monomer (E)

[0053] To a flask was added 5.0g(2.913mmol) of octa(trichlorosilylethyl)-POSS and diluted with 500ml of tetrahydrofuran, followed by addition of 7.78g(76.893mmol) of triethylamine. Next, the flask was cooled to -78°C, and 2.464g (76.893mmol) of methyl alcohol was slowly added thereto, and then it was slowly warmed to room temperature. The reaction was continued at room temperature for 20hrs, filtered through celite, and then volatile materials were evaporated from the filtrate under a reduced pressure of about 0.1Torr. Subsequently, 100ml of pentane was added to the filtrate and stirred for 1hr, and then the mixture was filtered through celite to provide a clear colorless solution. Finally, pentane was evaporated from this solution under a reduced pressure of about 0.1Torr to afford monomer (E) represented by the following formula:



[0054] The results obtained from NMR analysis of monomer (E) dissolved in CDCl<sub>3</sub> are as follows:

<sup>1</sup>H-NMR(300MHz): δ 0.66-0.69(m, 32H, 8x-CH<sub>2</sub>CH<sub>2</sub>-), 3.58(s, 72H, 8x-[OCH<sub>3</sub>]<sub>3</sub>)

### Example 1: Synthesis of siloxane-based resins

#### Example 1-1: Copolymerization of cyclic and cage-shape siloxane monomers

[0055] Cyclic and cage-shape siloxane monomers were quantified respectively according to Table 1, and then added to a flask, followed by dilution with 45ml of tetrahydrofuran. Thereafter, the flask was cooled to -78°C, and HCl and deionized water were slowly added thereto at the same temperature, and then it was slowly warmed to 70°C. The reaction was continued at 70°C for 16hrs, and transferred to a separatory funnel, followed by addition of 90ml of diethylether. After washing with 3X50ml of deionized water, volatile materials were evaporated from the remaining solution to afford a white powdery polymer. The powder was dissolved in a small amount of acetone, and filtered through a 0.2μm syringe filter so as to remove impurities to provide a clear filtrate. After addition of water to the filtrate, the resulting white powder was separated from the liquid phase(mixed solution of acetone and water), and then dried at a temperature of 0-5°C under a reduced pressure of about 0.1Torr to afford a fractionated siloxane-based resin.

Table 1

Resin	Monomers		HCl (mmol)	H <sub>2</sub> O (mmol)	Yield (g)
	Cyclic siloxane	Cage-shape siloxane			
(a)	Monomer (A) 13.294mmol	Monomer (C) 1.476mmol	1.713	570.96	6.15
(b)	Monomer (A) 12.142mmol	Monomer (D) 1.349mmol	1.673	557.56	6.04
(c)	Monomer (B) 12.136mmol	Monomer (D) 1.349mmol	1.673	557.56	5.17
(d)	Monomer (A) 11.183mmol	Monomer (E) 1.242mmol	1.640	546.70	4.11

**Example 1-2: Copolymerization of cyclic and cage-shape siloxane monomers together with a silane monomer of formula (3)**

[0056] Cyclic and cage-shape siloxane monomers as well as tetramethoxysilane as a silane monomer of formula (3) were quantified respectively according to Table 2, and then added to a flask, followed by dilution with 50ml of tetrahydrofuran. Thereafter, the flask was cooled to -78°C, and HCl and deionized water were slowly added thereto at the same temperature, and then it was slowly warmed to 60°C. The reaction was continued at 60°C for 16hrs, and transferred to a separatory funnel, followed by addition of 150ml of diethylether. After washing with 3X50ml of deionized water, volatile materials were evaporated from the remaining solution to afford a white powdery polymer. The powder was dissolved in a small amount of acetone, and filtered through a 0.2µm syringe filter so as to remove impurities to provide a clear filtrate. After addition of water to the filtrate, the resulting white powder was separated from the liquid phase (mixed solution of acetone and water), and then dried at a temperature of 0-5°C under a reduced pressure of about 0.1Torr to afford a fractionated siloxane-based resin.

Table 2

Resin	Monomers (mmol)			HCl (mmol)	H <sub>2</sub> O (mmol)	Yield (g)
	Cyclic siloxane	Cage-shape siloxane	Silane			
	Monomer (A)	Monomer (C)	Tetramethoxysilane			
(e)	10.799	1.200	5.144	1.598	532.494	5.37

**Example 1-3: Copolymerization of cyclic and cage-shape siloxane monomers together with silane monomers of formulas (3) and (4)**

[0057] The procedure of Example 1-3 was conducted according to the same manner as in the above Example 1-2, except that methyltrimethoxysilane was additionally used as a silane monomer of formula (4).

Table 3

Resin	Monomers (mmol)				HCl (mmol)	H <sub>2</sub> O (mmol)	Yield (g)
	Cyclic siloxane	Cage-shape siloxane	Silane				
	Monomer (A)	Monomer (C)	Tetramethoxysilane	Methyltrimethoxysilane			
(f)	9.598	1.200	5.144	1.197	1.490	496.428	4.76

**Example 1-4: Copolymerization of a cyclic siloxane monomer together with a silane monomer of formula (3)**

[0058] The procedure of Example 1-4 was conducted according to the same manner as in the above Example 1-2, except that the cage shape siloxane monomer was omitted.

Table 4

Resin	Monomers (mmol)		HCl (mmol)	H <sub>2</sub> O (mmol)	Yield (g)
	Cyclic siloxane	Silane			
	Monomer (A)	Tetramethoxysilane			
(g)	5.999	0.667	0.747	248.828	2.39
(h)	5.999	2.571	0.823	274.213	2.46
(i)	5.999	5.999	0.960	319.915	2.53

**Example 1-5: Copolymerization of a cyclic siloxane monomer together with silane monomers of formulas (3) and (4)**

[0059] The procedure of Example 1-5 was conducted according to the same manner as in the above Example 1-4, except that methyltrimethoxysilane was additionally used as a silane monomer of formula (4).

Table 5

Resin	Monomers (mmol)			HCl (mmol)	H <sub>2</sub> O (mmol)	Yield (g)
	Cyclic siloxane	Silane				
	Monomer (A)	Tetramethoxysilane	Methyltrimethoxysilane			
(j)	10.799	5.144	1.197	1.538	512.466	5.04

**Example 1-6: Copolymerization of a cage-shape siloxane monomer together with a silane monomer of formula (4)**

[0060] The procedure of Example 1-6 was conducted according to the same manner as in the above Example 1-1, except that a silane monomer of formula (4), methyltrimethoxysilane was used instead of the cyclic siloxane monomer.

Table 6

Resin	Monomers		HCl (mmol)	H <sub>2</sub> O (mmol)	Yield (g)
	Cage-shape siloxane	Silane			
(k)	Monomer (C) 1.476mmol	Methyltrimethoxysilane 13.287mmol	0.00517	172.36	2.03
(l)	Monomer (D) 1.349mmol	Methyltrimethoxysilane 12.113mmol	0.00580	193.36	1.95

**Example 2: Analysis of the composition of resins**

[0061] The respective siloxane-based resins obtained from the above Examples 1-1 through 1-6 were analyzed for weight average molecular weight(hereinafter, referred to as "Mw"), molecular weight distribution(hereinafter, referred to as "MWD"), weight loss, and contents of Si-OH, Si-OCH<sub>3</sub> and Si-CH<sub>3</sub>, as described below. The results are set forth in Table 7.

Table 7

Resin	MW	MWD	Si-OH (%)	Si-OCH <sub>3</sub> (%)	Si-CH <sub>3</sub> (%)	Weight loss (%)
(a)	63418	6.13	26.3	0.7	73.0	4.5
(b)	66614	8.59	37.6	0.6	61.8	4.1
(c)	89860	8.34	39.7	0.8	59.5	3.8
(d)	67145	7.86	28.6	1.7	69.7	3.7
(e)	60452	8.70	17.2	0.8	82.0	N.D. <sup>1)</sup>
(f)	54213	7.86	21.6	2.0	76.4	N.D.
(g)	29316	7.85	35.1	1.3	63.6	N.D.
(h)	26778	7.46	37.1	1.5	61.4	N.D.
(i)	19904	6.30	27.1	1.5	71.4	N.D.
(j)	23654	6.53	28.3	1.9	69.8	N.D.
(k)	6878	6.15	12.9	0.9	86.2	4.2

1) N.D.: not determined

# EP 1 245 642 A1

Table 7 (continued)

Resin	MW	MWD	Si-OH (%)	Si-OCH <sub>3</sub> (%)	Si-CH <sub>3</sub> (%)	Weight loss (%)
(1)	6904	5.70	30.6	1.4	68.0	4.6

[Analytical methods]

[0062]

- Mw and MWD: analyzed by gel permeation chromatography(Waters Co.)
- Si-OH, Si-OCH<sub>3</sub> and Si-CH<sub>3</sub> contents(%): analyzed by NMR (Bruker Co.)

$$\text{Si-OH}(\%) = \frac{\text{Area}(\text{Si-OH})}{\text{Area}(\text{Si-OH}) + \text{Area}(\text{Si-OCH}_3) + \text{Area}(\text{Si-CH}_3)} \times 100$$

$$\text{Si-OCH}_3(\%) = \frac{\text{Area}(\text{Si-OCH}_3)}{\text{Area}(\text{Si-OH}) + \text{Area}(\text{Si-OCH}_3) + \text{Area}(\text{Si-CH}_3)} \times 100$$

$$\text{Si-CH}_3(\%) = \frac{\text{Area}(\text{Si-CH}_3)}{\text{Area}(\text{Si-OH}) + \text{Area}(\text{Si-OCH}_3) + \text{Area}(\text{Si-CH}_3)} \times 100$$

- Weight loss(%): analyzed by a thermogravimetric analyzer(TA instruments Co.)

## Example 3: Measurement of thickness, refractive index and dielectric constant of resinous films

[0063] With or without being mixed with a porogen, heptakis(2,3,6-tri-O-methyl)-β-cyclodextrin in a mixing ratio by weight according to Table 8, each of the siloxane-based resins obtained from the above Examples 1-1 through 1-6 was dissolved, respectively, in either methylisobutylketone(MIBK) or propylene glycol methyl ether acetate(PGMEA), so that final concentration of the solid matter(inclusive of the resin and the porogen) in the resulting resinous solution amounted to 25wt%. The resinous solution was spin-coated onto a silicon wafer for 30sec with maintaining the spin rate of 3,000rpm. Under a nitrogen atmosphere, the coated wafer was subjected to sequential soft baking on a hot plate for 1min at either 100°C (for resin e, f, g, h, i, j) or 150°C(for resin a, b, c, d, k, l) and for another minute at 250°C, to remove the organic solvent sufficiently. Thereafter, the temperature of the wafer was elevated to either 400°C(for resin a, b, c, d, k, l) or 420°C(for resin e, f, g, h, i, j) at a rate of 3°C/min under vacuum condition, and then the wafer was cured at the same temperature for 1hr to afford a test piece.

[0064] Each of the test pieces thus prepared was analyzed for film thickness by using a prism coupler, an ellipsometer, and a profiler. Also, dielectric constant of the film was determined by using Hg CV meter(SSM 490i CV system, Solid State Measurements), at a frequency of approximately 1MHz in the gate voltage range of -220V through 220V as follows. Capacitance of a control piece coated with a reference material(e.g. thermal silicon oxide), whose film thickness and dielectric constant had been previously determined, was first measured. Then, contact area between a Hg electrode and the control piece was calculated from the following equation (1) and set down as a reference value:

$$A = C \times t / k \quad (1)$$

(wherein, "A" is the contact area between the Hg electrode and the control piece, "C" is the capacitance of the control piece measured above, "t" is the film thickness of the control piece, and "k" is the dielectric constant of the reference material(3.9 for thermal silicon oxide used herein).

[0065] Once capacitance of the test piece is found out from C-V measurement by using the Hg CV meter, film thickness of the test piece corresponding to the reference dielectric constant k=3.9, based on the capacitance and the reference "A", is determined from the above equation (1), and hereinafter referred to as "conversion thickness". Subsequently, the conversion thickness( $t_{\text{conv}}$ ) and the real film thickness( $t_{\text{test piece}}$ ) of the test piece, which was previously determined as described above, are substituted into the following equation (2), to provide dielectric constant "k" of the test piece:

# EP 1 245 642 A1

$$k_{\text{test piece}} = 3.9 \times t_{\text{test piece}} / t_{\text{conv.}}$$

(2)

[0066] The dielectric constants thus determined are set forth in Table 8 together with the film thickness.

Table 8

Resin	Resinous solution	R:P <sup>1)</sup>	Solvent	Prism coupler		Ellipsometer		Profiler	Dielectric constant
				T <sup>2)</sup> (Å)	R <sup>3)</sup>	T (Å)	R		
(a)	(a)	100:0	MIBK	8168	1.433			7751	2.26
(b)	(b)		"	8676	1.426	8700	1.426	8246	2.34
(c)	(c)		"	8050	1.435			7961	2.31
(d)	(d)		"	8565	1.427			8412	2.42
(e)	(e)		PGMEA	12190	1.4263	12230	1.430	11968	2.42
	(e-1)	70:30	"	10606	1.3463	10651	1.345	10521	2.29
(f)	(f)	100:0	"	9164	1.4364	9224	1.433	9095	2.47
	(f-1)	70:30	"	9806	1.3465	9901	1.340	9767	2.27
(g)	(g)	100:0	"	10032	1.4333	10125	1.431	9931	2.49
	(g-1)	90:10	"	9674	1.3921	9855	1.386	9536	2.35
	(g-2)	50:50	"	10282	1.3109	10230	1.315	10103	1.67
(h)	(h)	100:0	"	9428	1.4339	9589	1.433	9321	2.64
	(h-1)	90:10	"	9344	1.3966	9252	1.395	9341	2.41
	(h-2)	70:30	"	9425	1.3510	9411	1.321	9420	2.17
(i)	(i)	100:0	"	9208	1.4312	9380	1.432	9100	2.65
	(i-1)	90:10	"	9099	1.3964	9112	1.384	9056	2.49
	(i-2)	70:30	"	9781	1.3435	9653	1.311	9653	2.26
	(i-3)	50:50	"	10738	1.3125	10023	1.309	10562	1.51
(j)	(j)	100:0	"	8518	1.4414	8574	1.441	8514	2.51
	(j-1)	70:30	"	8432	1.3356	8534	1.330	8234	2.31
(k)	(k)	100:0	MIBK	7335	1.420	7367	1.422	6584	2.30
(l)	(l)	100:0	"	7535	1.424	7644	1.423	7055	2.34

1) resin:porogen(w/w)

2) thickness

3) refractive index

## Example 4: Analysis of resinous films for mechanical properties

### Example 4-1: Measurement of hardness and modulus of resinous films

[0067] Some of the resinous films formed in the above Example 3 were analyzed for hardness and modulus by using Nanoindenter II (MTS Co.). The film was indented until the indentation depth reached 10% of its whole thickness, which had been previously measured by use of a prism coupler. At this time, to secure the reliability of this measurement, 6 points were indented every test piece, and mean hardness and modulus were determined from a load-displacement curve. The results are set forth in Table 9.

Table 9

Resinous solution	Mechanical properties	
	Hardness(Gpa)	Modulus(Gpa)
(e)	0.85	4.93
(e-1)	0.38	2.87
(f)	0.89	5.57
(f-1)	0.37	2.79
(g)	1.00	6.16
(g-1)	0.72	4.56
(g-2)	0.34	2.74
(h)	1.06	6.36
(h-1)	0.83	4.70
(h-2)	0.54	3.78
(i)	1.04	6.62
(i-1)	0.82	5.07
(i-2)	0.48	3.52
(i-3)	0.38	2.90
(j)	1.06	6.72
(j-1)	0.46	3.29

#### Example 4-2: Measurement of crack-free thickness of resinous films

[0068] Siloxane-based resin (i) obtained from the above Example 1, and a mixture of resin (i):heptakis(2,3,6-tri-O-methyl)- $\beta$ -cyclodextrin=7:3(w/w) were dissolved in propylene glycol methyl ether acetate(PGMEA), respectively, varying final concentration of the solid matter in the respective resinous solutions to 25, 27, 29, 31, 33, and 35wt%. Each of the resinous solutions was spin-coated onto a silicon wafer at a spin rate of 3,000rpm for 30sec. Under a nitrogen atmosphere, the coated wafer was baked on a hot plate for 1 min at 100° C and for another minute at 250°C, to remove the organic solvent sufficiently. Next, the temperature of the wafer was elevated to 420°C at a rate of 3°C/min under vacuum condition, and then the resinous coating film on the surface of the wafer was cured at the same temperature for 1hr to afford a test piece. In order to find crack-free thickness, the resinous film of the test piece was observed with an optical microscope. The results are set forth in Table 10.

Table 10

R:P <sup>1)</sup>	Crack-free thickness( $\mu$ m)
100:0	1.7
70:30	1.5

1) resin (i):heptakis(2,3,6-tri-O-methyl)- $\beta$ -cyclodextrin(w/w)

#### Example 5: Analysis of resinous films for thermal stability

[0069] Siloxane-based resin (i) obtained from the above Example 1, and a mixture of resin (i):heptakis(2,3,6-tri-O-methyl)- $\beta$ -cyclodextrin=50:50(w/w) were dissolved in propylene glycol methyl ether acetate(PGMEA), respectively, at final concentration of 25wt%. Each of the resinous solutions was spin-coated onto a silicon wafer at a spin rate of 3,000rpm for 30sec. Under a nitrogen atmosphere, the coated wafer was baked on a hot plate for 1 min at 100°C and for another minute at 250°C, to remove the organic solvent sufficiently. Subsequently, the temperature of the wafer was elevated to 420°C at a rate of 3°C/min under vacuum condition, and then the wafer was cured at the same temperature for 1hr to afford a test piece. Film thickness and refractive index of the test piece were measured by use of a

prism coupler. Thereafter, the temperature elevation and curing were repeated twice in the same manner as described above, followed by the measurement of film thickness and refractive index of the test piece. Change rates of thickness and refractive index of the respective films are set forth in Table 11.

Table 11

R:P <sup>1)</sup>	Thickness(Å)		R.I.	
	Mean	Change rate(%) <sup>2)</sup>	Mean	Change rate(%) <sup>3)</sup>
100:0	9732	0.21	1.437	0.07
50:50	13714	1.65	1.332	0.19

1) resin (I):heptakis(2,3,6-tri-O-methyl)-β-cyclodextrin(w/w)


2) change rate of thickness(%) = [thickness of the film cured once - thickness of the film cured three times] ÷ thickness of the film cured once × 100

3) change rate of refractive index(%) = [refractive index of the film cured once - refractive index of the film cured three times] ÷ refractive index of the film cured once × 100


[0070] As described above, siloxane-based resins of the present invention are useful for forming low dielectric insulating film between interconnect layers in semiconductor devices, which is excellent in mechanical properties, thermal stability and resistance to crack.



#### Claims

1. A siloxane-based resin prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1) and a cage-shape siloxane compound of any of formulas (2a) through (2c), optionally with at least one silane compound, in an organic solvent in the presence of a catalyst and water, wherein the silane compound is substituted at Si with at least one hydrolysable group:




wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; p is an integer from 3 to 8; and m is an integer from 1 to 10;








35 in the above formulas (2a) through (2c), each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo; and  $n$  is an integer from 1 to 12.

- 40 2. The siloxane-based resin according to claim 1, wherein the resin is prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1) and a cage-shape siloxane compound of any of formulas (2a) through (2c), in an organic solvent in the presence of a catalyst and water:




55 wherein,  $R$  is  $H$ ,  $C_{1-3}$  alkyl,  $C_{3-10}$  cycloalkyl, or  $C_{6-15}$  aryl; each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo;  $p$  is an integer from 3 to 8; and  $m$  is an integer from 1 to 10;






in the above formulas (2a) through (2c), each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo; and  $n$  is an integer from 1 to 12.

3. The siloxane-based resin according to claim 1, wherein the resin is prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1) and a cage-shape siloxane compound of any of formulas (2a) through (2c), together with a silane compound of formula (3) and/or a silane compound of formula (4), in an organic solvent in the presence of a catalyst and water:



wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; p is an integer from 3 to 8; and m is an integer from 1 to 10;






in the above formulas (2a) through (2c), each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo; and  $n$  is an integer from 1 to 12;




wherein, each of  $X_1$ ,  $X_2$ ,  $X_3$ , and  $X_4$  is, independently,  $C_{1-10}$  alkoxy, or halo;



wherein,  $R$  is H,  $C_{1-3}$  alkyl,  $C_{3-10}$  cycloalkyl, or  $C_{6-15}$  aryl; and each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo.

- 35
4. The siloxane-based resin according to claim 1, wherein the resin is prepared by hydrolyzing and polycondensing a cyclic siloxane compound of formula (1), together with a silane compound of formula (3) and/or a silane compound of formula (4), in an organic solvent in the presence of a catalyst and water:




50

wherein,  $R$  is H,  $C_{1-3}$  alkyl,  $C_{3-10}$  cycloalkyl, or  $C_{6-15}$  aryl; each of  $X_1$ ,  $X_2$ , and  $X_3$  is, independently,  $C_{1-3}$  alkyl,  $C_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo;  $p$  is an integer from 3 to 8; and  $m$  is an integer from 1 to 10;




wherein, each of  $X_1$ ,  $X_2$ ,  $X_3$ , and  $X_4$  is, independently,  $C_{1-10}$  alkoxy, or halo;




(4)

wherein, R is H, C<sub>1-3</sub> alkyl, C<sub>3-10</sub> cycloalkyl, or C<sub>6-15</sub> aryl; and each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo.


5. The siloxane-based resin according to claim 1, wherein the resin is prepared by hydrolyzing and polycondensing a cage-shape siloxane compound of any of formulas (2a) through (2c), together with a silane compound of formula (3) and/or a silane compound of formula (4), in an organic solvent in the presence of a catalyst and water:



(2a)



(2b)




(2c)

in the above formulas (2a) through (2c), each of X<sub>1</sub>, X<sub>2</sub>, and X<sub>3</sub> is, independently, C<sub>1-3</sub> alkyl, C<sub>1-10</sub> alkoxy, or halo, provided that at least one is alkoxy or halo; and n is an integer from 1 to 12;



wherein, each of  $\text{X}_1$ ,  $\text{X}_2$ ,  $\text{X}_3$ , and  $\text{X}_4$  is, independently,  $\text{C}_{1-10}$  alkoxy, or halo;



wherein, R is H,  $\text{C}_{1-3}$  alkyl,  $\text{C}_{3-10}$  cycloalkyl, or  $\text{C}_{6-15}$  aryl; and each of  $\text{X}_1$ ,  $\text{X}_2$ , and  $\text{X}_3$  is, independently,  $\text{C}_{1-3}$  alkyl,  $\text{C}_{1-10}$  alkoxy, or halo, provided that at least one is alkoxy or halo.

6. The siloxane-based resin according to any of claims 1 to 5, wherein the organic solvent is an aromatic hydrocarbon solvent, an aliphatic hydrocarbon solvent, a ketone-based solvent, an ether-based solvent, an acetate-based solvent, an alcohol-based solvent, a silicon-based solvent, or a mixture thereof.
7. The siloxane-based resin according to any of claims 1 to 6, wherein the catalyst is hydrochloric acid, nitric acid, benzene sulfonic acid, oxalic acid, formic acid, potassium hydroxide, sodium hydroxide, triethylamine, sodium bicarbonate, pyridine, or a mixture thereof.
8. The siloxane-based resin according to any of claims 1 to 7, wherein 0.00001-10mol of the catalyst is added per 1mol of the monomers to be polycondensed.
9. The siloxane-based resin according to any of claims 1 to 8, wherein 0.1-1000mol of water is added per 1mol of the monomers to be polycondensed.
10. The siloxane-based resin according to any of claims 1 to 9, wherein the hydrolysis and polycondensation are performed at 0-200° C for 0.1-100hrs.
11. The siloxane-based resin according to any of claims 1 to 10, wherein  $\text{Si-OR}$  (wherein, R is H,  $\text{C}_{1-3}$  alkyl,  $\text{C}_{3-10}$  cycloalkyl, or  $\text{C}_{6-15}$  aryl) content of the resin is more than 5mol%.
12. The siloxane-based resin according to any of claims 1 to 11, wherein Mw of the resin is between 3,000 and 500,000.
13. A method for forming insulating film between interconnect layers in semiconductor devices, wherein the method comprises the steps of:
  - providing a resinous solution by dissolving the siloxane-based resin according to any of claims 1 to 12 in an organic solvent;
  - coating a silicon wafer with the resinous solution; and
  - heat-curing the resulting coating film.
14. The method according to claim 13, wherein the organic solvent is an aliphatic hydrocarbon solvent, an aromatic hydrocarbon solvent, a ketone-based solvent, an ether-based solvent, an acetate-based solvent, an alcohol-based solvent, an amide-based solvent, a silicon-based solvent, or a mixture thereof.
15. The method according to claim 13 or 14, wherein content of the siloxane-based resin in the resinous solution is 0.1-80wt%.
16. The method according to any of claims 13 to 15, wherein the resinous solution further comprises a porogen, wherein weight ratio of the siloxane-based resin vs. the porogen is between 99:1 and 30:70.
17. The method according to claim 16, wherein the porogen is cyclodextrin, polycaprolactone, or a derivative thereof.
18. The method according to claim 16 or 17, wherein total content of the siloxane-based resin and the porogen in the resinous solution is 0.1-80wt%.
19. The method according to any of claims 13 to 18, wherein the heat-curing is performed at 150-600° C for 1-150min.



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 02 25 1958

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 727 817 A (TEXAS INSTRUMENTS INC) 21 August 1996 (1996-08-21) * examples *	1-19	C08L83/04 C08J9/26 H01B3/46 H01L21/316 H01L21/312
A	EP 0 750 337 A (DOW CORNING) 27 December 1996 (1996-12-27) * examples *	1-19	
A	US 5 942 638 A (LICHTENHAN JOSEPH D ET AL) 24 August 1999 (1999-08-24) * the whole document *	1-19	
A	US 5 484 867 A (LICHTENHAN JOSEPH D ET AL) 16 January 1996 (1996-01-16) * column 1, line 24 - column 10, line 22; claims; examples *	1-19	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08L C08J H01B H01L C09D
The present search report has been drawn up for all claims			
Place of search <b>MUNICH</b>		Date of completion of the search <b>14 May 2002</b>	Searcher <b>Kollitz, R</b>
CATEGORY OF CITED DOCUMENTS		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons A: technological background O: non-written disclosure P: intermediate document	
X: particularly relevant: if taken alone Y: particularly relevant: if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document			

EPO FORM 1504 (04-02) (Prelim)

EP 1 245 642 A1

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 25 1958

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

14-05-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0727817	A	21-08-1996	US 5656555 A	12-08-1997
			EP 0727817 A2	21-08-1996
			JP 8250490 A	27-09-1996
			US 5665849 A	09-09-1997
EP 0750337	A	27-12-1996	US 5635240 A	03-06-1997
			EP 0750337 A2	27-12-1996
			JP 9022903 A	21-01-1997
			TW 379246 B	11-01-2000
			US 5776599 A	07-07-1998
US 5942638	A	24-08-1999	NONE	
US 5484867	A	16-01-1996	US 5412053 A	02-05-1995
			US 5589562 A	31-12-1996

EPO FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82